



APR 29 2002

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Application of

Nakamura et al.

Serial No.: 09/746,228

Group Art Unit: 1762

Filed: December 26, 2000

Examiner: Markham, W.

For: TRANSPARENT LAMINATE, METHOD FOR PRODUCING THE SAME, AND
PLASMA DISPLAY PANEL

Honorable Assistant Commissioner of Patents
Washington, D.C. 20231

#6/A
Gueda
5/4/02
(NE)

AMENDMENT UNDER 37 C.F.R. §1.111
AND
RESPONSE TO RESTRICTION REQUIREMENT

RECEIVED
MAY 02 2002
TC 1700

Sir:

In response to the Office Action mailed February 1, 2002, please amend the above-identified application as follows:

IN THE SPECIFICATION:

Please replace Page 10, lines 1-22 with the following paragraph:

In the above transparent laminate, preferably, the laminate further comprises a low-refractive-index transparent thin film deposited on the surface of the transparent substrate, the low-refractive-index transparent thin film having a refractive index n_L in a range of from 1.3 to 1.6 and having a thickness of $550 \text{ nm} \times (1/4 n_L) \times (1 \pm 0.15)$. In the above transparent laminate according, preferably, the laminate further comprises a low-refractive-index transparent thin film deposited on a surface of the high-refractive-index transparent thin film located as the outermost layer, the low-refractive-index transparent thin film having a refractive index n_L in a range of from 1.3 to 1.6 and having a thickness of $550 \text{ nm} \times (1/2 n_L) \times (1 \pm 0.15)$. Further, in place of such a low-refractive-index transparent thin film, the above transparent laminate further comprises any one of an anti-reflection film, an anti-mirroring film and a low-reflection anti-mirroring film stuck on to the surface of the high-refractive-index transparent thin film located as the outermost layer, through a transparent adhesive

R